



NEPCOAT Qualified Products List A

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

DataMine		Slip	Manuf'r Coating	VOC	QPL
System	3-COAT SYSTEM	Coef	DFT (min/max)	Tested	Accepted
No.	Coats	Class	mil micron	g/L	Dates
	TESTED AND ACCEPTED				

NEPCOAT LIST A - INORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish

SSC(19)-03	CARBOLINE COMPANY					from
Primer	Carbozinc® 11 HS Inorganic Zinc Primer	B ¹	2-6	50-150	289	12/10/20
Interm	Carboguard® 893 Epoxy Intermediate		3-6	75-150	225	until mtg.
Topcoat	Carbothane® 133 LV Aliphatic Polyurethane		3-5	75-125	252	fall 2027
¹ Footnote	6 mils max DFT, 18 hrs min cure, 12% max thinner					

- ¹ Footnote Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.
- NOTE 1 NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT
- AASHTO DataMine. See Structural Steel Coating test data at <https://datamine.transportation.org>.
 - Accelerated lab and field testing of coating systems is performed according to AASHTO R-31 criteria.
 - Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.
 - SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.
 - VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.
 - Recommended DFT values are listed by manufacturer (see Product Data Sheets.)
 - Any change in coating formulation from that tested will result in removal of the system from the QPL.
 - The full QPL term is seven years starting from the date of acceptance until the next biannual NEPCOAT meeting.
 - * Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.
- Note that R-31-09 Section 12.1, Requalification Testing, has been discontinued.
- es VOC value adjusted for exempt solvents



NEPCOAT Qualified Products List B

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

DataMine	Slip	Manuf'r Coating	VOC	QPL
System	Coef	DFT (min/max)	Tested	Accepted
No. Coats	Class	mil micron	g/L	Dates
3-COAT SYSTEM				
TESTED AND ACCEPTED				
NEPCOAT LIST B - ORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish				
SSC(24)-02 *		SHERWIN WILLIAMS COMPANY		from
SSC(15)-07 Primer	Zinc Clad® 4100 Organic Zinc Rich Epoxy Primer	B ¹	3-5 75-125 306	10/7/25
Interm	Macropoxy® 646 Fast Cure Epoxy		3-10 75-250 251	until mtg.
Topcoat	Hi-Solids Polyurethane 250		3-5 75-125 287	fall 2029
¹ Footnote	5 mils max DFT, 72 hours min cure, 5% max thinner			
SSC(18)-08		WASSER COATINGS		from
SSC(10)-05 Primer	MC-Zinc 100	B ¹	3-5 75-125 140 es	10/01/19
Interm	MC-Miomastic 100		3-5 75-125 106 es	until mtg.
Topcoat	MC-Ferrex A 100		2-4 50-100 149 es	fall 2026
¹ Footnote	5.5 mils max DFT, 72 hrs min cure, 10% max thinner			
SSC(18)-09		SHERWIN WILLIAMS COMPANY		from
Primer	Zinc Clad® 4100 Organic Zinc Rich Epoxy Primer	B ¹	3-5 75-125 336	10/01/19
Interm	Macropoxy® 646 Fast Cure Epoxy		3-10 75-250 229	until mtg.
Topcoat	Acrolon™ 218 HS Acrylic Polyurethane		3-6 75-150 276	fall 2026
¹ Footnote	5 mils max DFT, 72 hours min cure, 5% max thinner			
SSC(19)-02		CARBOLINE COMPANY		from
Primer	Carbozinc® 859 Organic Zinc Rich Epoxy Primer	B ¹	3-10 75-250 342	12/10/20
Interm	Carboguard® 893 Epoxy Intermediate		3-6 75-150 218	until mtg.
Topcoat	Carbothane® 133 LV Aliphatic Polyurethane		3-5 76-127 254	fall 2027
¹ Footnote	6 mils max DFT, 6 days min cure, 10% vol max thin			
(continues)	(List B continues)			
¹ Footnote	Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.			
NOTE 1	NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT			
2	AASHTO DataMine. See Structural Steel Coating test data at https://datamine.transportation.org .			
3	Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.			
4	Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.			
5	SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.			
6	VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.			
7	Recommended DFT values are listed by manufacturer (see Product Data Sheets.)			
8	Any change in coating formulation from that tested will result in removal of the system from the QPL.			
9	The full QPL term is <u>seven</u> years starting from the date of acceptance until the next biannual NEPCOAT meeting.			
*	Acceptance is <u>CONDITIONAL</u> pending submission within <u>four</u> years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.			
	Note that R-31-09 Section 12.1, Requalification Testing, has been discontinued.			
es	VOC value adjusted for exempt solvents			



NEPCOAT Qualified Products List B

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

DataMine		Slip	Manuf'r Coating	VOC	QPL	
System	3-COAT SYSTEM	Coef	DFT (min/max)	Tested	Accepted	
No.	Coats	Class	mil micron	g/L	Dates	
NEPCOAT LIST B - ORGANIC Zinc Rich Primer / Epoxy or Urethane Intermediate / Aliphatic Urethane Finish						
SSC(22)-04 *	PPG INDUSTRIES				from	
Primer	SIGMAZINC™ 70 DOT	B ¹	2-7	50-177	257	10/03/23
Interm	PPG DTM EPOXY 202 DOT		4-8	100-200	234	until mtg.
Topcoat	PITTHANE ULTRA DOT 95-812 SERIES		2-3	50-75	250 es	fall 2027
¹ Footnote	7 mils max DFT, 24 hrs. min cure, 10% vol max thin					
SSC(22)-01 *	PPG INDUSTRIES					from
Primer	SIGMAZINC™ 75 DOT	Failed ¹	2-7	50-177	277	10/03/23
Interm	AMERLOCK 600 DOT	To	3-10	125-250	232	until mtg.
Topcoat	PITTHANE ULTRA DOT 95-812 SERIES	Meet B	2-3	50-75	242 es	fall 2027
¹ Footnote	7 mils max DFT, 48 hrs. min cure, 10% vol max thin					
	Note: Not suitable for use in slip-critical connections.					



NEPCOAT Qualified Products List C

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

DataMine		Slip	Manuf'r Coating	VOC	QPL
System	2-COAT SYSTEM	Coef	DFT (min/max)	Tested	Accepted
No.	Coats	Class	mil micron	g/L	Dates
	TESTED AND ACCEPTED				

NEPCOAT LIST **C** - ORGANIC Zinc Rich Primer / ----- / Topcoat

SSC(18)-03	SHERWIN WILLIAMS COMPANY					from
Primer	Zinc Clad® 4100 Organic Zinc Rich Epoxy Primer	B ¹	3-5	75-125	318	04/02/19
Interm	---		---	---	---	until mtg.
Topcoat	Sher-Loxane 800 Polysiloxane		4-6	100-150	122	spring 2026
¹ Footnote	5 mils max DFT, 72 hours min cure, 5% thinner					

- ¹ Footnote Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.
- NOTE 1 NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT
- 2 AASHTO DataMine. See Structural Steel Coating test data at <https://datamine.transportation.org>.
 - 3 Accelerated lab and field testing of coating systems is performed according to AASHTO R-31 criteria.
 - 4 Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.
 - 5 SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.
 - 6 VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.
 - 7 Recommended DFT values are listed by manufacturer (see Product Data Sheets.)
 - 8 Any change in coating formulation from that tested will result in removal of the system from the QPL.
 - 9 The full QPL term is seven years starting from the date of acceptance until the next biannual NEPCOAT meeting.
 - * Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.
- Note that R-31-09 Section 12.1, Requalification Testing, has been discontinued.
- es VOC value adjusted for exempt solvents



NEPCOAT Qualified Products List D

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

DataMine		Slip	Manuf'r Coating	VOC	QPL
System	2-COAT SYSTEM	Coef	DFT (min/max)	Tested	Accepted
No.	Coats	Class	mil micron	g/L	Dates
	TESTED AND ACCEPTED				

NEPCOAT LIST **D** - INORGANIC Zinc Rich Primer / ----- / Topcoat

- ¹ Footnote Information from the Slip-Coefficient and Creep Resistance Test Certificate is given for use w/ primed bolted connections.
- NOTE 1 NEPCOAT- NORTHEAST PROTECTIVE COATINGS COMMITTEE of CT, DE, ME, MA, NH, NJ, NY, PA, RI, VT
- 2 AASHTO DataMine. See Structural Steel Coating test data at <https://datamine.transportation.org>.
- 3 Accelerated lab and field testing of coating systems is performed according to AASHTO NTPEP R-31 criteria.
- 4 Systems are accepted for use on NEW and 100% BARE EXISTING steel for bridges cleaned by abrasive blasting.
- 5 SSC(yr)-xx systems comply with AASHTO R-31 Evaluation Practice & NEPCOAT Acceptance Criteria.
- 6 VOC values are lab test results using unthinned samples. NEPCOAT max VOC limit is 420 g/L (3.5 lb/gal). Individual state requirements for VOC limits may differ.
- 7 Recommended DFT values are listed by manufacturer (see Product Data Sheets.)
- 8 Any change in coating formulation from that tested will result in removal of the system from the QPL.
- 9 The full QPL term is seven years starting from the date of acceptance until the next biannual NEPCOAT meeting.
- * Acceptance is CONDITIONAL pending submission within four years of successful 2-year field history. A startup list of five bridges painted with the paint system must be submitted within two years. See Acceptance Criteria.
- Note that R-31-09 Section 12.1, Requalification Testing, has been discontinued.
- es VOC value adjusted for exempt solvents



NEPCOAT Acceptance Criteria List A, B, C, D

for Protective Coatings for
NEW and 100% BARE EXISTING Steel for Bridges

AASHTO R31-Testing Standard & NEPCOAT Acceptance Criteria (3/16/04, 2/15/05, 10/16/08, 4/7/09, 10/12/11, 4/4/23)

*** PERFORM ALL REQUIRED TESTS FOR EACH COATING SYSTEM. ***

TEST NO. 1 - SLIP COEFFICIENT - Perform Slip Co test on the same primer batch used for the other tests.
- The Slip Co test results may be applied to more than one system provided all Primer samples come from the same container.

Primer	(min.)
IOZ	Acceptance criteria: Required to have Class B Slip coefficient min. 0.5
OZ	Acceptance criteria: None. Report results only. Class B Slip Co. recommended but not required.

TEST NO. 2 - SALT FOG RESISTANCE (ASTM B117)

Delamination	Acceptance criteria: no delamination allowed
Rust / Blistering	Acceptance criteria (max.):

//----- RUST CRITERIA -----//

-- BLISTER CRITERIA--

Primer	System	@ Hrs	max creep	ave creep	% length	in scribe	@ Hrs	Convers'n #
IOZ	P-I-T	5000	4 mm	2 mm	not req'd	not req'd	4000	8
OZ	P-I-T	5000	8 mm	4 mm	not req'd	not req'd	4000	7

TEST NO. 3 - CYCLIC WEATHERING RESISTANCE (ASTM D5894)

Delamination	Acceptance criteria: no delamination allowed
Rust / Blistering	Acceptance criteria (max.):

//----- RUST CRITERIA -----//

-- BLISTER CRITERIA--

Primer	System	@ Hrs	max creep	ave creep	% length	in scribe	@ Hrs	Convers'n #
IOZ	P-I-T	5040	4 mm	2 mm	not req'd	not req'd	4032	9
OZ	P-I-T	5040	8 mm	4 mm	not req'd	not req'd	4032	8

GLOSS value	Acceptance criteria: Report results only
GLOSS % Retent'n	Acceptance criteria: Report results only
COLOR Change, Δe	Acceptance criteria: Report results only

TEST NO. 4 - ABRASION RESISTANCE (ASTM D4060) – NOT REQUIRED

Weight Loss	Acceptance criteria: Test discontinued
Wear Index	Acceptance criteria: Test discontinued

TEST NO. 5 - ADHESION (ASTM D4541)

Pull-Off Strength	Acceptance criteria (min.) for both primer and PIT panels:
IOZ	6.9 MPa (1,000 psi)
OZ	6.9 MPa (1,000 psi)

TEST NO. 6 - FREEZE THAW STABILITY

Pull-Off Strength	Acceptance criteria: achieve min. Test 5 req'd PIT adhesion results and fall within 60% of Test 5 values
-------------------	--

(continued)



NEPCOAT Acceptance Criteria List A, B, C, D

for Protective Coatings for NEW and 100% BARE EXISTING Steel for Bridges

AASHTO R31-09 Testing Standard & NEPCOAT Acceptance Criteria (3/16/04, 2/15/05, 10/16/08, 4/7/09, 10/12/11)

TEST NO. 7 - COATING IDENTIFICATION TESTS

VOC	Acceptance criteria:	Max. 420 g/L (3.5 lb/gal). Individual state requirements may differ.
Coating properties	Acceptance criteria:	Report only
Coating thickness	Acceptance criteria:	A 2-coat system shall be tested and applied at min. total 9 mils DFT.

TEST NO. 8 - ATMOSPHERIC EXPOSURE (TWO YEAR) at outdoor site: – NOT REQUIRED

Acceptance criteria: Test discontinued

ITEM NO. 9 - FIELD HISTORY (TWO YEAR)

Acceptance criteria: (All systems after SSC 06-05) The coating manufacturer shall submit two notifications;

- (1) a startup list within two years of product acceptance identifying five bridges (in a cold/wet climatic region) which have been coated with a minimum of 400 liters (100 gallons) of the coating system (i.e. total volume of primer, intermediate and topcoat); and
- (2) the same list of bridges within four years of product acceptance after the system has two years (min.) of successful field performance. "Successful performance" is simply defined as whether the Owner is satisfied with its application and performance to date, and whether the Owner would recommend the use of the coating again.

PRODUCT VERIFICATION TESTING

AASHTO R-31-09 Appendix X1 recommends that the Owner perform product verification testing for determining if the coatings supplied to a project are the same quality as the manufacturer's materials originally tested and certified for acceptance.

The R-31-09 Test 7- Coating Identification Tests are described in Sect. 9.7 and Appendix X1, and the lab test results are given in AASHTO DataMine (<https://datamine.transportation.org/>) along with the manufacturer's listed values.

When the Owner performs verification testing, the following tolerances apply:

Verification Test	R-31-09 Section	R-31-09 App X1	ASTM Test	DataMine Test 7	Tolerance *
Total solids (% by mass)	9.7.9.1	X1.1.1.6	D 2369	Line 2	± 5 %
Pigment (% by mass)	9.7.9.5	X1.1.1.8	D 2371	" 3	± 5 %
Mass per volume (g/L)	9.7.9.8	X1.1.1.5	D 1475	" 6	± 2 %
Viscosity (Stormer)	9.7.9.9	X1.1.1.4	D 562	" 7	± 8 %

* The tolerance is applied to the DATAMINE "test result" value (not the manufacturer's "listed value").

These tolerances apply to the primer and intermediate coats each in their mixed condition (not Part A, Part B components). For topcoats, if the color is different from the original color in DataMine testing, then these tolerances apply to the Owner's verification test values the first time a particular color is used.

Note 1. Test Criteria: Two of three panels must pass for each test to pass. (e.g. Tests 2, 3, 5, 6)

Note 2. Materials: NEPCOAT does not accept waterborne coatings for the QPL for use in the Northeast States.

Note 3. Field History: If available, include an existing bridge(s) with field-applied coatings.